



MUBW- FUSED MULLITE

FUSED MULLITE (AL₂O₃ - SiO₂) FOR REFRACTORIES

ABOUT:

MUBW is an extremely pure fused mullite obtained from fusion of silica sand and alumina in an electric arc furnace. It presents low iron contamination, low thermal expansion, high thermal shock resistance and high temperature strength. It is an excellent material for investment casting and other refractory applications.

TYPICAL CHEMICAL ANALYSIS	
Al ₂ O ₃	73.10%
SiO ₂	26.30
Fe ₂ O ₃	0.03
Na ₂ O	0.40
CaO	0.06

TYPICAL PHYSICAL PROPERTIES	
Crystal Structure:	Orthorhombic
Melting Point:	1850° C
Color:	Grey
Specific Gravity:	3.08 g/cc
Average Crystal Size:	2,000 µm
Reversible Linear Expansion:	0.85% at 1400° C
Apparent Porosity:	3.0%
Apparent Specific Density:	3.04 g/cm ³

App. Porosity & App. Specific Density by ASTM C 20-00

AVAILABLE SIZES	
MESH	METRIC (mm)
3/4" x 5/16"	19.1 - 8.00
5/16" x 4	8.00 - 4.75
4 x 10	4.75 - 2.00
10 x 20	2.00 - 0.850
10 x 40	2.00 - 0.425
20 x 40	0.850 - 0.425
40 x 200	0.425 - 0.075
TPF II	- 0.212
200 MF	- 0.075
325 MF	- 0.045
*Other sizes available upon request	

The information contained in this data sheet has been determined through the application of accepted engineering practice and is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results to be obtained from use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will make your own tests to determine the suitability of the product for your particular use.

USEM

U.S. ELECTROFUSED MINERALS, INC.

600 Steel Street, Aliquippa, PA 15001

Phone: 800-927-8823

email: info@usminerals.com

www.usminerals.com



ELECTRO ABRASIVES

701 Willet Road, Buffalo, NY 14218

Phone: 716-822-2500

Email: info@electroabrasives.com

www.electroabrasives.com



GRUPO CURIMBABA

Updated: 04/13