

SPECIAL SINTERED BAUXITE

SINTERED BAUXITE (AL₂O₃) FOR WELDING FLUXES

ABOUT:

Sintered bauxite with medium Iron Oxide levels. Used in the manufacture of welding flux.

TYPICAL CHEMICAL ANALYSIS

Al ₂ O ₃	83.50%
TiO ₂	0.71
SiO ₂	8.70
Fe ₂ O ₃	6.28
CaO	0.02
K ₂ O	0.23
P	0.03

MINERALOGICAL CHARACTERISTICS

Corundum - α -Al₂O₃
Mullite - 3-Al₂O₃ - 2-SiO₂
Hematite - Fe₂O₃

AVAILABLE SIZES

80 / Finer, 100 / Finer, 325 / Finer

USEM

U.S. ELECTROFUSED MINERALS, INC.

600 Steel Street, Aliquippa, PA 15001

Phone: 800-927-8823

email: info@usminerals.com

www.usminerals.com



**ELECTRO
ABRASIVES**

701 Willet Road, Buffalo, NY 14218

Phone: 716-822-2500

Email: info@electroabrasives.com

www.electroabrasives.com



GRUPO CURIMBABA

Updated: 04/13

The information contained in this data sheet has been determined through the application of accepted engineering practice and is believed to be reliable. Since the conditions of application and use of our products are beyond our control, no warranty is expressed or implied regarding accuracy of the information, the results to be obtained from use of the product, or that such use will not infringe on any patent. This information is furnished with the express condition that you will make your own tests to determine the suitability of the product for your particular use.